FG600 Photoluminescent

Glow-in-the-dark

Luminescent Value:

| The initial lighting source is 100LX, Activating time is 15 minutes, | | |
|--|---|-------------|
| the luminescent value at 5 seconds | ≥ | 8000 mcd/m2 |
| the luminescent value at 30 minutes | ≥ | 45 mcd/m2 |
| the luminescent value at 60 minutes | ≥ | 20 mcd/m2 |
| the luminescent value at 480 minutes | ≥ | 2.0 mcd/m2 |
| the luminescent value at 600 minutes | ≥ | 1.5 mcd/m2 |

Service life: 10 years indoor, 7 years outdoor Specification: 1.24m x 45.7m Available colours: Light Green

Other technical dates:

- 1. Surface Film: Acrylic type
- Thickness of film: 0.22mm, thickness of glue: 0.04mm
 Thickness of release paper: 0.18mm
 Total thickness of product: 0.44mm
- 3. Weight of release paper: 160g/sqm with 5% more or less
- 4. Type of adhesive: Pressure-Sensitive Type
- 5. Strength of adhesive: after sticking to board for 24 hours, at the condition of 0.8kg, 5 min, total length: 10cm, the falling length \leq 2cm
- 7. Working temperature: -20 \square ----60 \square



Tel: 01827 300500 sales@grafityp.co.uk Web: www.grafityp.co.uk