Siser Heat Transfer Vinyl

FLOCK PRO®

SPECIFICATIONS

	Composition	Average Thickness	Carrier	Oeko-Tex	Certifications	
Stripflock Pro standard colors*	PVC	650 microns	Adhesive Polyester	class I	OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 18.HIT.56690 HOHENSTEIN HTTI	REACH n° 1907/2006/EU
Stripflock Pro fluo colors	PU	620 microns		class II	OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 19.HIT.98675 HOHENSTEIN HTTI	VEGANOK AZIENDA N. 1004

*Stripflock Pro black Oeko-Tex standard 100 class II

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	60°	60 gf	15 cm/sec	15 seconds	155°C (311°F)	Medium (2,5/3,5 bar)	warm

→ **Mirror cut the design**
→ **Weed excess material**
→ **Place the design on the garment**
→ **Heat apply at the conditions shown above**
→ **Peel carrier warm**

PRODUCT HIGHLIGHTS
→ **velvet touch**
→ **embroidery look**

NOTE: Stripflock Pro cannot be layered on itself. We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, inside-out	YES inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

→ **Wait 24 hours after the application before the first wash**
→ **Respect the textile recommendations**
→ **Do not bleach or use aggressive chemical agents**

GRAFITYP UK Limited