




REFLEX COLOUR

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	160-190 microns	Adhesive polyester	<p>REACH n° 1907/2006/EU</p> <p>    </p>

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	from 70 to 100 with new blade, 110 with used blade	20 cm/sec	5+10 seconds	155°C (311°F)	Medium (2,5/3,5 bar)	warm

- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier warm

PRODUCT HIGHLIGHTS

- Easy to cut and weed
- Adhesive carrier helps cutting small details
- 8 colors available

 **NOTE:** We highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, best inside-out	YES best inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents