

REFLEX SILVER

SPECIFICATIONS

Composition	± Avarage Thickness	Q Carrier	♣ Certifications		
	160-170 microns	Adhesive polyester	REACH n° 1907/2006/EU		
PU			OEKO-TEX ® CONFIDENCE IN TEXTILES STANDARD 100 19.HIT.86736 HOHENSTEIN HTTI		

APPLICATION INSTRUCTIONS

⊘ Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated	△ Blade	<u></u> Pressure	>> Speed	Time	Temperature	Pressure	Peel
and dye sublimated textiles)	45°	70-100gf with new blade, 110gf with used blade	20 cm/sec	5+10 seconds	155°C (311°F)	Medium (2,5/3,5 bar)	warm

- → Mirror cut the design
- → Weed excess material
- ightarrow Place the design on the garment
- ightarrow Heat apply at the conditions shown above
- → Peel carrier warm

PRODUCT HIGHLIGHTS

- → High retroreflectivity power
- → Adhesive carrier helps cutting small details
- → Easy to cut and weed
- → Follows EN ISO 20471 regulation
- $oldsymbol{\mathcal{L}}$ NOTE: We highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	∮ ► Position
Up to 60°C, best inside-out	YES best inside-out	YES (cotton cycle)	YES	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents



Tel: 01827 300500 Web: www.grafityp.co.uk E-mail: sales@grafityp.co.uk