

BLACKBOARD®

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	95 microns	adhesive polyester	<p>REACH n° 1907/2006/EU</p> <p>OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 18.HIT.41690 HOHENSTEIN HTTI</p> <p>VEGANOK AZIENDA N. 1004</p> <p>VEGANOK</p>

APPLICATION INSTRUCTIONS

APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	70 gf	20 cm/sec	15 seconds	135°C (275°F)	Medium (2,5/3,5 bar)	hot

- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier hot

PRODUCT HIGHLIGHTS

- Re-writable
- Perfect for advertising
- Soft touch

 **NOTE:** We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, inside-out	YES inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents