

BRICK® 1000

SPECIFICATIONS

*• Composition	± Average Thickness	Q Carrier	A Certifications		
	1000 microns	non adhesive polyester	REACH n° 1907/2006/EU		
PU			OEKO-TEX ® CONFIDENCE IN TEXTILES STANDARD 100 15.HIT.75859 HOHENSTEIN HTTI		

APPLICATION INSTRUCTIONS

	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	<u></u> Pressure	>> Speed	Time	Temperature	Pressure	Peel
	60°	150 gf	10 cm/sec	25 seconds	155°C (311°F)	Medium/High (2,5/>3,5 bar)	cold

- → Mirror cut the design
- → Weed excess material
- \rightarrow Place the design on the garment
- → Heat apply at the conditions shown above
- → Peel carrier cold

PRODUCT HIGHLIGHTS

- → Our thickest product
- → Adds dimension to any logo
 - NOTE: We highly recommend to perform a test, before launching a production!

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	∮ ⊳ Position
Up to 60°C, best inside-out	YES best inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents



Tel: 01827 300500 Web: www.grafityp.co.uk E-mail: sales@grafityp.co.uk