

BRICK® 600

SPECIFICATIONS

c	Average Thickness	Q	♣		
Composition		Carrier	Certifications		
PU	600 microns	Non adhesive Polyester	REACH n° 1907/2006/EU OEKO-TEX ® CONFIDENCE IN TEXTILES STANDARD 100 15.HIT.75859 HOHENSTEIN HTTI		

APPLICATION INSTRUCTIONS

⊘ APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated	Blade	<u></u> Pressure	» Speed	Time	Temperature	Pressure	€ Peel
`and dye sublimated textiles)	60°	80 gf	10 cm/sec	25 seconds	155°C (311°F)	medium/high (2,5-3,5 bar)	cold

- → Mirror cut the design
- → Weed excess material
- > Place the design on the garment
- → Heat apply at the conditions shown above
- → Peel carrier cold

PRODUCT HIGHLIGHTS

- → Thick product
- → Adds dimension to any logo
- → Matt finish

$oldsymbol{\mathcal{L}}$ NOTE: We highly recommend to perform a test, before launching a production!

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	∮ Position
Up to 60°C, best inside-out	YES best inside- out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- ightarrow Do not bleach or use aggressive chemical agents



Tel: 01827 300500 Web: www.grafityp.co.uk E-mail: sales@grafityp.co.uk