


# P.S. PERFORATED

## SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	90 microns	Adhesive polyester	<p>REACH n° 1907/2006/EU</p> <p>OEKO-TEX® CONFIDENCE IN TEXTILES <b>STANDARD 100</b> 084270.0 CENTROCOT</p> <p>VEGANOK AZIENDA N. 1004</p> 

## APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/ cotton blends (not suited for treated and dye sublimated textiles)	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	80 gf	30 cm/sec	15 seconds	150°C (302°F)	Medium (2,5/3,5 bar)	hot

- Cut the material mirrored
- Peel off excess material
- Place the decoration on the garment
- Apply following the recommended parameters
- Remove the carrier while hot

### PRODUCT HIGHLIGHTS

- Breathable
- Reduced thickness
- Micro-perforated surface

 **NOTE:** We highly recommend to perform a test before launching a production

## CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, best inside-out	YES best inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents