

P.S. STRETCH-EASYWEED STRETCH

SPECIFICATIONS

Composition	Average Thickness	Q Carrier	Certifications
PU	90 microns	adhesive polyester	REACH n° 1907/2006/EU OEKO-TEX ® CONFIDENCE IN TEXTILES STANDARD 100 1202341.0 CENTROCOT

APPLICATION INSTRUCTIONS

⊘ Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/ cotton blends,elastan (not suited for treated	Blade	<u></u> Pressure	>> Speed	Time	Temperature	Pressure	Peel
`and dye sublimated textiles)	45°	50 gf	20 cm/sec	20 seconds	160°C (320°F)	Medium (2,5/3,5 bar)	hot

- → Cut the material mirrored
- → Peel off excess material
- → Place the decoration on the garment
- → Apply following the recommended parameters
- ightarrow Remove the media while hot

ADVANTAGES OF THE PRODUCT

- → Reduced thickness
- → Matte Finish
- → High elasticity

NOTE: We highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	∮ Position
Up to 60°C, best inside- out	YES best inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents



Tel: 01827 300500 Web: www.grafityp.co.uk E-mail: sales@grafityp.co.uk