










TWINKLE

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	235 microns	Adhesive polyester	REACH n° 1907/2006/EU  

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)							
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	150-170 gf	15 cm/sec	15 seconds	150°C (302°F)	Medium (2,5/3,5 bar)	cold









- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier cold

PRODUCT HIGHLIGHTS

- Smooth glitter surface
- Silicone-like touch
- Reflective appearance when exposed to light

 **NOTE:** We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

							
Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 40°C, inside-out	YES inside-out	YES (synthetic cycle)	---	Up to 2 years	Between 18 and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents