










P.S. METALLIC

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	100 microns	Adhesive polyester	REACH n° 1907/2006/EU  

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/ cotton blends (not suited for treated and dye sublimated textiles)							
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	60°	130 gf	15 cm/sec	15 seconds	160°C (320°F)	Medium (2,5/3,5 bar)	cold

- Cut the material mirrored
- Peel off excess material
- Place the decoration on the garment
- Apply following the recommended parameters
- Remove the carrier when cold

PRODUCT HIGHLIGHTS

- Metallic effect
- Glossy almost mirrored like finish

 NOTE: We highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Handwash	YES best inside-out	NO	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents