

# C-PRINT® PU EXTRA

## SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	70 microns	non adhesive polyester	REACH n° 1907/2006/EU <b>OEKO-TEX®</b> CONFIDENCE IN TEXTILES <b>STANDARD 100</b> 1400240.0 CENTROCOT

## APPLICATION INSTRUCTIONS

APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
nylon, polyester, treated fabrics, leather	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	75 gf	25 cm/sec	15 seconds	155°C (311°F)	Medium (2,5/3,5 bar)	hot

- Print, cut and peel off excess material
- Remove the print from the carrier with the help of TTD Easy
- Place the decoration on the fabric
- Apply following the recommended parameters
- Remove the TTD while hot

### PRODUCT HIGHLIGHTS

- Available in glossy or matte version
- Very Thin Product
- Applicable on difficult fabrics (nylon, leather, tnt)

**NOTE:** Given the large number of inks and printers, we highly recommend to perform a test before launching a production

## CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 40°C, best inside-out	NO	YES (synthetic cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents