

# C-PRINT® PU+

## SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	80 microns	non adhesive polyester	<p>OEKO-TEX® CONFIDENCE IN TEXTILES STANDARD 100 1400240.0 CENTROCOT</p> <p>REACH n° 1907/2006/EU</p> <p>VEGANOK AZIENDA N. 1004</p> <p>Certified for HP Latex Inks</p> <p>PU MATT not Latex certified</p>

## APPLICATION INSTRUCTIONS

APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/ cotton blends, elastan (not suited for treated and dye sublimated textiles)	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	65 gf	25 cm/sec	15 seconds	155°C (329°F)	Medium (2,5/3,5 bar)	hot

- Print, cut and peel off excess material
- Remove the print from the carrier with the help of TTD Easy
- Place the decoration on the fabric
- Apply following the recommended parameters
- Remove the TTD while hot

### PRODUCT HIGHLIGHTS

- Available in glossy and matte version
- Thin and Soft to the Touch
- Slightly elastic

**NOTE:** Given the large number of inks and printers, we highly recommend to perform a test before launching a production

## CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, best inside-out	YES best inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents