

EcoStretch™

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	85-90 microns	Adhesive polyester	

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
cotton, polyester, poly/cotton blends, elastan (Not suited for treated and dye sublimated textiles)	45°	50-60 gf	20 cm/sec	5 seconds	120°C (248°F)	Medium (2,5/3,5 bar)	hot

- Cut and weed the material
- Recommendation: Preheat the lower platen at 120°C for 5 seconds
- Place the decoration on the garment
- Apply following the recommended parameters
- Remove the carrier hot

PRODUCT HIGHLIGHTS

- Very low transfer temperature and quick application
- Waterbased compound
- Elastic material



NOTE: We highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 40°C, best inside-out	YES best inside-out	YES (mix)	NO	Up to 2 years	Between 18 and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents